



Sani-Tech® SPT-60L Pump Tubing for High Accuracy Applications

Pump Tubing for Accurate Dispensing

Sani-Tech® SPT-60L is a premium platinum-cured silicone tubing designed for the most exacting pharma operations where low spallation, long pump life and high accuracy are required. Sani-Tech® SPT-60L provides best-in-class accuracy and precision assuring consistent filling performance and reducing the potential for costly over/under fills.

With an average pump life over *250 hours, Sani-Tech® SPT-60L tubing outperforms competitive extruded silicone tubing providing improved performance and reliability under various pumping conditions. (*Testing was performed on Sani-Tech® SPT-60L tubing using a four-roller peristaltic pump head operating at 400rpm with no backpressure at room temperature).

Filling Accuracy (Target) and Precision (Repeatability)

Sani-Tech® SPT-60L was assessed for accuracy (dispensing target fill volume) and precision (repeatability of delivered volume) against competitive pump tubing marketed for filling applications. Sani-Tech® SPT-60L provided a *4X improvement in filling accuracy and 2X improvement in precision over the closest performing competitor tubing. (*Supplemental data presented in white paper.)

Low Spallation

Sani-Tech® SPT-60L has the lowest spallation (number of particles and area of particles) across multiple dispensing cycles among the various silicone pump tubing evaluated.

Biocompatible

Sani-Tech® SPT-60L tubing is manufactured from platinum-cured silicone materials and tested to a variety of specifications including:

ADCF/BSE/TSE statements	ISO 10993-3 / ISO 10993-5
USP <88> Class VI	EP 3.1.9

Visit www.biopharm.saint-gobain.com to download the [Technical Dossier](#).

Features / Benefits

- Long Pump Life
- Low Spallation
- Accurate and Consistent Dispensing
- Full Extractables Report per BioPhorum Operations Group (BPOG) Protocol
- Technical Dossier Available
- Available with ValPlus™ Certification (See page 4 for more details)

Typical Applications

- Final Fill
- Extended Duration Pumping
- Precision Pumping

Sani-Tech® SPT-60L Pump Tubing Standard Size

Part Number	ID inch (mm)	OD inch (mm)	Wall Thickness inch (mm)	Burst Pressure (psi)	Burst Pressure (Bar)
SPT60L-031-1	0.031 (0.8)	0.094 (2.4)	0.031 (0.8)	*159	11.0
SPT60L-031-2	0.031 (0.8)	0.157 (4.0)	0.063 (1.6)	189	13.0
SPT60L-047-157	0.047 (1.2)	0.157 (4.0)	0.055 (1.4)	167	11.5
SPT60L-047-2	0.047 (1.2)	0.173 (4.4)	0.063 (1.6)	174	12.0
SPT60L-063-1	0.063 (1.6)	0.125 (3.2)	0.031 (0.8)	113	7.8
SPT60L-063-157	0.063 (1.6)	0.157 (4.0)	0.047 (1.2)	141	9.7
SPT60L-063-2	0.063 (1.6)	0.187 (4.8)	0.063 (1.6)	*159	11.0
SPT60L-079-204	0.079 (2.0)	0.204 (5.2)	0.063 (1.6)	145	10
SPT60L-094-2	0.094 (2.4)	0.220 (5.6)	0.063 (1.6)	133	9.1
SPT60L-125-1	0.125 (3.2)	0.187 (4.8)	0.031 (0.8)	66	4.6
SPT60L-125-2	0.125 (3.2)	0.250 (6.4)	0.063 (1.6)	113	7.8
SPT60L-125-268	0.125 (3.2)	0.268 (6.8)	0.071 (1.8)	122	8.4
SPT60L-157-315	0.157 (4.0)	0.315 (8.0)	0.079 (2)	113	7.8
SPT60L-187-1	0.187 (4.8)	0.250 (6.4)	0.031 (0.8)	45	3.1
SPT60L-187-2	0.187 (4.8)	0.313 (8.0)	0.063 (1.6)	84	5.8
SPT60L-187-346	0.187 (4.8)	0.346 (8.8)	0.079 (2.0)	100	6.9
SPT60L-187-3	0.187 (4.8)	0.375 (9.5)	0.094 (2.4)	113	7.8
SPT60L-187-4	0.187 (4.8)	0.438 (11.1)	0.125 (3.2)	133	9.2
SPT60L-197-4	0.197 (5.0)	0.472 (12)	0.138 (3.5)	136	9.4
SPT60L-236-394	0.236 (5.9)	0.394 (10.0)	0.079 (2.0)	84	5.8
SPT60L-250-1	0.250 (6.4)	0.313 (8.0)	0.031 (0.8)	34	2.3
SPT60L-250-2	0.250 (6.4)	0.375 (9.5)	0.063 (1.6)	64	4.4
SPT60L-250-3	0.250 (6.4)	0.438 (11.1)	0.094 (2.4)	*93	6.4
SPT60L-250-4	0.250 (6.4)	0.500 (12.7)	0.125 (3.2)	115	7.9
SPT60L-313-2	0.313 (8.0)	0.438 (11.1)	0.063 (1.6)	54	3.7
SPT60L-313-3	0.313 (8.0)	0.500 (12.7)	0.094 (2.4)	77	5.3
SPT60L-313-488	0.313 (8.0)	0.488 (12.4)	0.087 (2.2)	73	5.0
SPT60L-375-2	0.375 (9.5)	0.500 (12.7)	0.063 (1.6)	50	3.4
SPT60L-375-3	0.375 (9.5)	0.563 (14.3)	0.094 (2.4)	69	4.8
SPT60L-375-4	0.375 (9.5)	0.625 (15.9)	0.125 (3.2)	84	5.8
SPT60L-438-3	0.438 (11.1)	0.625 (15.9)	0.094 (2.4)	57	4.0
SPT60L-500-2	0.500 (12.7)	0.625 (15.9)	0.063 (1.6)	33	2.2
SPT60L-500-4	0.500 (12.7)	0.750 (19.1)	0.125 (3.2)	*62	4.2

*Actual Tested Burst Pressure Part Numbers
Burst Pressure Test Method = ASTM D1599
Test Media = Water

The values listed for burst pressures are derived from tests conducted under controlled laboratory conditions. Many factors will reduce the tubing's ability to withstand pressures, including temperature, chemical attack, stress, pulsation and the attachment to fittings. It is imperative that the user conduct tests simulating the conditions of the application prior to specifying the tubing for use.

Typical Physical Properties

Property	ASTM Method	Target Values
Durometer, Shore A	D2240	60 nominal
Tensile Strength, psi	D412	> 900
Elongation, %	D412	> 300
Specific Gravity	D792	1.12 nominal

Unless otherwise noted, all tests were conducted at controlled room temperature. Values shown were determined on 0.075" thick extruded strip or 0.075" thick molded ASTM plaques or molded ASTM durometer buttons.

General Sterilization Methods


- Autoclavable
- Gamma Irradiation - up to 5.0 Mrad (50 kGy)
- Gas - Ethylene Oxide

Test data based on open source literature for material compatibility.

Peristaltic Pump Tubing Life

Due to its specific formulation, Sani-Tech® SPT-60L provides exceptional continuous pumping duration. As demonstrated in Table 1, Sani-Tech® SPT-60L provides over 3x the pump life compared to other extruded silicone tubing that are marketed for final fill applications.

Table 1



Pumping hours until tubing rupture for 1/16" x 3/16" ID x OD (1.6 x 4.8 mm) silicone tubing. A four-roller peristaltic pump head was utilized, operating at 400rpm (with no back pressure at room temperature).

Vial Fill Accuracy and Precision (Non-Irradiated Tubing)

Table 2 demonstrates the degradation in vial fill accuracy from the nominal (1.8 mL) target with the number of vial fills. Sani-Tech® SPT-60L maintains higher precision compared to competitors' tubing throughout the duration of the filling trial. (See white paper for more details.)

Table 2




A 10 point moving average represents the trend in data. It smooths out data by averaging the first 10 data points (for example, 1-10, 2-11, 3-12, 4-13, etc.).

Spallation

Using flow-imaging microscopy, spallation within the fluid path was measured as the number of particles produced (number of particles/ml) and the relative size of the particles generated ($\mu\text{m}^2/\text{ml}$) over a number of simulated vial fills. The study was performed with Ultra-Pure water using a dual six-roller peristaltic pump, operating at 300 rpm (no back pressure at room temperature). The following table summarizes the spallation results for 1/16" x 3/16" ID x OD (1.6 x 4.8 mm) silicone tubing and represents the average sum of all particles produced after 3000 vial fills. The test was done in triplicate.

Sani-Tech® SPT-60L was tested against four final fill marketed silicone tubes and generated 50% less spallation (particles/ml) than the closest competitor.




2µm (micron) particle size was the minimum level of equipment detection.

ValPlus™ Certification

ValPlus™ provides customers with an industry first opportunity to mitigate risk and add value into their production process steps. This enhanced level of tubing validation certification offers a higher level of quality assurance in single-use fluid handling components. Saint-Gobain Life Sciences validates the fluid path of the tubing using a single, normal ANSI Level II sampling plan to meet the following standard industry requirements:

- USP <788> for Sub-visible Particulates
- USP <85> and <161> for Endotoxins
- ISO 11737-1 for Bioburden

For more information on ValPlus™, please visit www.biopharm.saint-gobain.com/valplus



Saint-Gobain
Life Sciences –
Bioprocess Solutions

Sani-Tech® SPT-60L
Additional Resources:

- [Extractables Report](#)
- [Technical Dossier](#)
- [ValPlus™ Certification Available](#)

Sani-Tech® is a registered trademark.

Uncontrolled Document - for the controlled version of this document please visit www.biopharm.saint-gobain.com

Contact us today for:
Consultations • Samples • Orders

For registered access to Saint-Gobain Technical Dossier
CLICK HERE



Saint-Gobain Life Sciences

3910 Terry Diane St.
Beaverton, MI 48612
Tel: (888) 387-0067
Fax: (989) 435-2355

www.biopharm.saint-gobain.com

IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain Performance Plastics products for all intended uses and that the materials to be used comply with all applicable medical regulatory requirements. Saint-Gobain Performance Plastics assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication or application of the products into which the materials are incorporated.

WARRANTY: For a period of 12 months from the date of first sale, Saint-Gobain Performance Plastics warrants this product to be free of defects in materials and workmanship. Our only obligation will be to replace any portion proving defective, or at our option, to refund the purchase price thereof.

SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.